



### SPECTRA 33 C

Spectra 33 C multi alloy films are carefully designed to act selectively on the spectrum of solar light, offering the best possible compromise between transparency and performance.



SOLAR SCREEN® Warranty  
**10 YEARS**



Fire-resistance rating  
**M1**



Storage from -5°C to +40°C  
**3 YEARS**



European Standard EN 1096-1  
**TESTED IN A  
LABORATORY**



REACH RoHS compliant  
**RESPECTED**

### WIDTHS AVAILABLE:

↔ **122 cm**

↔ **152 cm**

### TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (\*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	68 %
Reflection of external visible light	18 %
Reflection of internal visible light	15 %
Total solar energy rejected	59 %
Total solar energy rejected 2*	55 %
Solar ratio :	
Solar energy reflection	27 %
Solar energy absorption	36 %
Solar energy transmission	37 %
Reduction in Solar Glare	29 %
g-value	0.41
u-value	4.9
Rejected Infrared (760-2500 nm)	+/- 95 %
Shading coefficient	0.4
Installation type : Internal application	
Roll length	30,5 m
PET / PVC composition	PET
Thickness	40 µ

Colour : LIGHT CHAMPAGNE

### CONSTRUCTION

- "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
- High optical quality polyester, with anti IR metal particles deposit
- Bonding adhesive
- High optical quality polyester
- PS adhesive, glass polymerization within 15 days
- Protection release liner, disposable after installation



### INSTALLATION ADVICE

Vertical installation and on standard glass surface\*\*

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	!
Reflective tinted double pane	✓
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	!
STADIP INT. clear double pane	!

✓ Yes    ! Caution    ✗ Not recommended

\*Recommendations provided on the basis of a glazed surface covering up to 2.5m<sup>2</sup>, contact us for definitive details or to obtain a thermal chock analysis report.

### MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. sun pose 0808 or 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film. To prevent a possible oxidation of the metal alloys, it is mandatory to use our sealing varnish (reference number 0771) on the corners of the film, after installation.

*Non-contractual data, SOLAR SCREEN® reserves the right to modify the composition of its films at any time.*